



APTEK LABORATORIES, INC.

ISO 9001 / AS9100 Certified

28570 Livingston Avenue, Valencia, CA 91355-4171 • (661) 257-1677 FAX (661) 257-8939

TECHNICAL DATA & INFORMATION

APTEK® 6500-PMF

High purity, low outgassing, electrically conductive adhesive

PRODUCT DESCRIPTION

APTEK 6500-PMF is a one component, pre-mixed frozen, 100% solids, silver-filled epoxy adhesive specifically designed for microelectronic die attach applications.

KEY FEATURES AND BENEFITS

- High purity resin system for minimum level of ionic contamination to prevent corrosion problems
- High cross-link density to maintain stability and minimize outgassing during operational life even in high-vacuum environments and sealed packages
- Smooth, thixotropic consistency for machine stamping applications. Viscosity can be factory controlled for screening or dispensing applications.
- Contains no diluents or solvents to minimize formation of voids during cure

HANDLING INFORMATION

Work life in 5cc syringe after thaw @ 25°C, hours >16

Note: Viscosity increases slowly over time - approximately 20-30% over 8 hours duration. Actual work life to be determined by user for specific application.

Handling Notes

1. **APTEK 6500-PMF** syringes are shipped in dry ice. Upon receipt transfer frozen syringe to a storage freezer @ $\leq -40^{\circ}\text{C}$
2. To thaw remove a syringe from freezer and allow to warm to room temperature.
3. Do not place in oven or microwave - this will shorten use life.
4. Typical thaw time for 5cc syringe @25°C ambient is approximately 15-30 minutes.

CURE SCHEDULE

2 hrs @ 165°C

Note: Alternative cure schedules may be determined by the user depending on application requirements.

- DISCLAIMER NOTICE -

All statements, technical data, and recommendations expressed herein are based on tests believed to be reliable and accurate. However, APTEK LABORATORIES, INC. gives no warranty, expressed or implied, regarding the accuracy of this information. It is intended that the buyer and user of these products shall determine the suitability of the information provided for his specific application, and is responsible for its selection.

APTEK LABORATORIES, INC. shall not be liable for any injury, loss or damage, direct or consequential, arising out of the use or misuse of these products, or of the information given in these data bulletins. Purchasers assume all risk and liability whatsoever in connection with the use of these products and this information.

TYPICAL PROPERTIES

(values not to be used for specification purposes)

<u>CHARACTERISTICS</u>	<u>APTEK 6500-PMF</u>	<u>TEST METHOD</u>
Color	Silver gray	Visual
Viscosity @ 25°C, cps spindle/speed, (rpm)	25,000 #5/10	ASTM D-1824
Specific gravity	2.9	ASTM D-1475
Flash point, °C	>150	ASTM D-92
Shelf life @ -40°C, months factory sealed containers	6	
<u>CURED PHYSICAL PROPERTIES</u>	<u>APTEK 6500-PMF</u>	<u>TEST METHOD</u>
Hardness, durometer D	89	ASTM D-2240
Glass transition temp, °C	155	Perkin-Elmer TMS-2
Thermal coefficient of expansion, in/in/°C alpha 1 alpha 2	45 x 10 ⁻⁶ 147 x 10 ⁻⁶	Perkin-Elmer TMS-2 Perkin-Elmer TMS-2
Lap shear @ 25°C, Al to Al	2200	ASTM D-1002
Die shear @ 25°C, Ag to Si, 0.070" x 0.070" IC, psi	5700	MIL-STD 883-B
Thermal conductivity, (cal) (cm)/(sec-cm ² -°C)	40 x 10 ⁻⁴	COLORA
Outgassing @ 10 ⁻⁶ torr @ 125°C TML, % CVCM%	0.10 0.001	ASTM E-595 ASTM E-595
Residual gas analysis Hydrocarbons Ammonia Fluorocarbons	not detected not detected not detected	MIL-STD 883-B
Hydrolyzable ionic contaminants	<u>Ion</u>	<u>Extraction Level, ppm</u>
	Cl ⁻	<20
	Br ⁻	<2
	F ⁻	<2
	NH ₄ ⁺	<10
	K ⁺	<10
	Na ⁺	<20
	NO ₃ ⁻	<5
	PO ₄ ⁻	<5

Notes

- Sample ground to 40-60 mesh.
- 1 gm of sample to 50 gm of deionized water.
- Sample/water mixture refluxed 48 hrs @ 125°C, 15 psi.

CURED ELECTRICAL PROPERTIES**APTEK 6500-PMF****TEST METHOD**

Volume resistivity @25°C, ohm-cm

0.0002

ASTM D-257

SAFETY AND FIRST AID

APTEK 6500-PMF is a premixed frozen silver-filled epoxy blend which is safe to handle when used properly. The adhesive is packaged in sealed syringes and there should be no need to wet the adhesive. Avoid contact with skin and eyes and use in a well-ventilated area and avoid breathing vapors. In case of eye contact, flush with fresh clean water for at least 15 minutes; for skin contact, wash thoroughly with soap and water. If swallowed, drink at least one pint of water and call a physician. Refer to Material Safety Data Sheet for more details.

Revised: 12/09/09 – mv

Issued 3/30/98

APTEK[®] is a registered trademark of Aptek Laboratories, Inc.