



APTEK LABORATORIES, INC.

28570 Livingston Avenue, Valencia, CA 91355-4171 • (661) 257-1677 FAX (661) 257-8939

TECHNICAL DATA & INFORMATION

UVIKOTE™ 7503LM-A/B

UV Curing, Low Modulus, Low Outgassing, Urethane Conformal Encapsulant/Coating

PRODUCT DESCRIPTION

UVIKOTE 7503LM-A/B is a low viscosity, two component, electrically insulating, transparent, urethane coating designed for the encapsulation and protection of electrical/electronic components mounted on printed circuit boards. This system provides an excellent combination of flexibility and low modulus for demanding applications where the management of thermomechanical stresses is required.

UVIKOTE 7503LM-A/B coating will become tack free when exposed to the proper UV light radiation. The coating will fully post cure in exposed and shaded areas will continue to post cure in 14 days at 25°C and 50% relative humidity. As an alternative, the post cure for the coating in both exposed and shaded areas may be accelerated with low to moderate heat.

KEY FEATURES AND BENEFITS

- Qualified to Mil-I-46058C and IPC-C-830B
- Multicure mechanism for complete cure in shaded areas underneath components
- Excellent flexibility and low modulus for reduced stress in the encapsulation of sensitive components (e.g. glass-bodied diodes)
- Meets NASA condensable volatile requirements for high vacuum environments
- Highly reversion resistant for good physical stability under high heat and humidity environments
- Low Tg (-65°C) for excellent low temperature cycling, storage and performance
- Excellent adhesion to plastic/metal components and substrates. Adheres well to itself for multicoat and repair applications
- Ready-to-spray viscosity and long pot life for encapsulation and coating applications
- No TDI, no toxic solvents, no free acrylic acid for safety
- Also available as two component kits that can be stored at room temperature
- Complete companion UV product line available:
 - UVIKOTE™ 7503LMA-PMF for use in automated dispensing equipment (viscosity = 55-70 cps)
 - UVIKOTE 7504LM-PMF – 100% solids for thicker applications like back-side solder joint encapsulation
 - UVISTAKE™ 7205LM-PMF – thixotropic, non-flow adhesive for wire tacking and component staking

- DISCLAIMER NOTICE -

All statements, technical data, and recommendations expressed herein are based on tests believed to be reliable and accurate. However, APTEK LABORATORIES, INC. gives no warranty, expressed or implied, regarding the accuracy of this information. It is intended that the buyer and user of these products shall determine the suitability of the information provided for his specific application, and is responsible for its selection.

APTEK LABORATORIES, INC. shall not be liable for any injury, loss or damage, direct or consequential, arising out of the use or misuse of these products, or of the information given in these data bulletins. Purchasers assume all risk and liability whatsoever in connection with the use of these products and this information.

- APTEK 7503 Thinner – non-photosensitive, non-aromatic
- APTEK 7503 Stripper – low viscosity removal of cured coating/adhesive for repair operations
- APTEK 7503 Stripper Gel– thixotropic version for localized removal of cured coating/adhesive

HANDLING INFORMATION

Mix ratio, parts by weight: 100 (7503LM- A) / 100 (7503LM-B)

Work Life, @ 25°C, 200 gm mass, hrs. > 8

NOTES:

1. Work life adversely affected by heat and humidity as well as solvent evaporation.
2. Work life can be extended by additions of thinner and/or periodical replenishment with freshly mixed UVIKOTE 7503LM-A/B.
3. Once opened, Part A must be purged with dry air prior to resealing as it is moisture sensitive. **Do Not** purge Part B as this will deactivate the inhibitor.
4. Store Part A and Part B in original containers at 20-25°C.
5. Parts A and B are light sensitive. Care should be taken to avoid any excessive light exposure. It is recommended that containers be stored in a dark place whenever possible.

MIXING

Weigh 100 parts of UVIKOTE 7503LM Part A into a clean dry glass, metal, or plastic container and then add 100 parts of UVIKOTE 7503LM Part B. Machine mix on slow speed or hand stir with glass or metal stirrer until complete and thorough blending is achieved. Care should be taken to avoid any source of moisture contamination or air entrapment during mix.

Notes: 1. For best results and a bubble-free coating, vacuum mixture at less than 10mm Hg for no more than 30 seconds after "break" to avoid boiling the solvent from the mixture.

2. For thin coatings (≤3 mils) no solvent evaporation dwell time is usually required prior to UV exposure, thicker coatings may require a 10-30 minute dwell time to avoid a wrinkled surface after UV-exposure. Customer to test for each application to determine if solvent dwell time is necessary and if so, for how long.

CURE SCHEDULE

U.V. Cure with Conveyor Equipment

2 passes under 300 W/in Fusion UV, D-bulb lamp at rate of 1 foot per min. Bulb height above coating surface should be adjusted to expose the coating to approximately ~7.5 joules/cm² of radiation per pass.

U.V. Cure with Spot Cure Equipment

We recommend using an EFOS Novacure or equivalent equipment with similar power generating capabilities. This system is capable of generating the same amount of energy as in cure #1. In some applications, diffusers may be necessary to insure even energy distribution and complete cure. Customer should consult Aptek Laboratories and/or equipment supplier to optimize cure for individual applications.

Postcure

After curing as indicated in steps 1 or 2 above, the coating can be postcured as follows:

- a) 14 days at 25°C and 50% relative humidity
- OR
- b) 4 hours at 100°C, or 6 hours at 85°C, or 12 hours at 65°C

Note: The above cure schedules are conservative and should be used as guidelines only. User should determine proper cure schedule based on application requirements and properties desired.

TYPICAL PROPERTIES
(not for specification purposes)

<u>CHARACTERISTICS</u>	<u>7503LM-A/B</u>	<u>7503LM-B</u>	<u>TEST METHOD</u>
Color	Clear yellow/amber	Clear yellow/amber	Visual
Specific gravity	0.91	0.89	ASTM D-1475
Viscosity @ 25°C,cps	35	30	ASTM D-1824
Flash point, °C	>5°C	5°C	TCC
Shelf life @ 25°C, or below, months in factory sealed containers	6	6	
<u>CURED PHYSICAL PROPERTIES</u>	<u>7503LM-A/B</u>		<u>TEST METHOD</u>
Hardness, Durometer A	55A		ASTM D-2240
Glass transition temp., °C	-65		ASTM E831-86
Thermal coefficient of expansion, in/in/°C			
alpha 1	82 x 10 ⁻⁶		ASTM E831-86
alpha 2	222x 10 ⁻⁶		
Outgassing @ 10 ⁻⁶ Torr			
TML, %	0.80		ASTM E-595
CVCM, %	0.02		ASTM E-595
Young's modulus, psi			
@55°C	450		
@25°C	700		
@-40°C	9500		
Evidence of haze	None		ASTM E-595
Fungus resistance	Non-nutrient		ASTM G-21
<u>CURED ELECTRICAL PROPERTIES</u>	<u>7503LM-A/B</u>		<u>TEST METHOD</u>
Volume resistivity, @25°C, ohm-cm	4.0 x 10 ¹⁴		ASTM D-257
Dielectric constant, @1KHz, @25°C	3.2		ASTM D-150
Dissipation factor @1KHz, @25°C	0.03		ASTM D-150
Dielectric strength, 0.003" thick film, volts/mil	>1500		ASTM D-149
Insulation resistance, ohms	1.0 x 10 ¹⁴		MIL-I-46058C

SAFETY AND FIRST AID

UVIKOTE 7503LM-A is an unfilled organic isocyanate/acrylate blend resin containing solvent and is thus considered a flammable liquid and should be treated with caution. Avoid storage temperatures above 25°C and keep away from flame, sparks, or other sources of ignition. Use in well ventilated area and avoid breathing vapors. In case of eye contact, flush with fresh clean water for at least 15 minutes; for skin contact, wash thoroughly with soap and water. If swallowed, drink at least one pint of water and call a physician. Refer to Material Safety Data Sheet for more details.

UVIKOTE 7503LM-B is an organic polyol/acrylate blend containing solvent and is thus considered a flammable liquid and should be treated with caution. Avoid storage temperatures above 25°C and keep away from flame, sparks, or other sources of ignition. May cause severe eye and skin irritation with direct contact. Inhalation of vapors may result in breathlessness, severe coughing, chest discomfort, and irritation of mucous membranes. Avoid skin and eye contact and use in well ventilated, hooded area. In case of eye contact, flush profusely with fresh clean water and contact physician. For skin contact, wash thoroughly with soap and water. If inhaled, move subject to fresh air and provide fresh water to drink. If swallowed dilute, with at least one pint of water and contact physician immediately. Refer to Material Safety Data Sheet for more details.

UVIKOTE™ is a trademark of Aptek Laboratories, Inc
UVISTAKE™ is a trademark of Aptek Laboratories, Inc.
Issued: 6/22/07