



# APTEK LABORATORIES, INC.

ISO 9001 / AS9100 Certified

28570 Livingston Avenue, Valencia, CA 91355-4171 • (661) 257-1677 FAX (661) 257-8939

## TECHNICAL DATA & INFORMATION

### UVIKOTE™ 7503LM-PMF

UV Curing, Low Modulus, Low Outgassing, Urethane Conformal Encapsulant/Coating

#### PRODUCT DESCRIPTION

**UVIKOTE 7503LM-PMF** is a low viscosity, one component, premixed frozen liquid, electrically insulating, transparent, urethane coating designed for the encapsulation and protection of electrical/electronic components mounted on printed circuit boards. This system provides an excellent combination of flexibility and low modulus for demanding applications where the management of thermomechanical stresses is required.

**UVIKOTE 7503LM-PMF** coating will become tack free when exposed to the proper UV light radiation. The coating will fully post cure in both the exposed and shaded areas in 14 days at 25°C and 50% relative humidity. As an alternative, the post cure for the coating in both exposed and shaded areas may be accelerated with low to moderate heat.

#### KEY FEATURES AND BENEFITS

- Qualified to Mil-I-46058C and IPC-CC-830B
- Multicure mechanism for complete cure in shaded areas underneath components
- Excellent flexibility and low modulus for reduced stress in the encapsulation of sensitive components (e.g. glass-bodied diodes)
- Meets NASA condensable volatile requirements for high vacuum environments
- Highly reversion resistant for good physical stability under high heat and humidity environments
- Low Tg (-65°C) for excellent low temperature cycling, storage and performance
- Excellent adhesion to plastic/metal components and substrates. Adheres well to itself for multicoat and repair applications
- Ready-to-spray viscosity and long pot life for encapsulation and coating applications
- No TDI, no toxic solvents, no free acrylic acid for safety
- Also available as two component kits that can be stored at room temperature
- Complete companion UV product line available:
  - UVIKOTE™ 7503LMAUTO-PMF for use in automated dispensing equipment (viscosity = 55-70 cps)
  - UVIKOTE 7504LM-PMF – 100% solids for thicker applications like back-side solder joint encapsulation
  - UVISTAKE™ 7205LM-PMF – thixotropic, non-flow adhesive for wire tacking and component staking

#### **- DISCLAIMER NOTICE -**

All statements, technical data, and recommendations expressed herein are based on tests believed to be reliable and accurate. However, APTEK LABORATORIES, INC. gives no warranty, expressed or implied, regarding the accuracy of this information. It is intended that the buyer and user of these products shall determine the suitability of the information provided for his specific application, and is responsible for its selection.

APTEK LABORATORIES, INC. shall not be liable for any injury, loss or damage, direct or consequential, arising out of the use or misuse of these products, or of the information given in these data bulletins. Purchasers assume all risk and liability whatsoever in connection with the use of these products and this information.

- UVIKOTE T-100 Thinner – non-photosensitive, non-aromatic
- UVIKOTE S-100 Stripper – low viscosity removal of cured coating/adhesive for repair operations
- UVIKOTE S-200 Stripper – thixotropic version for localized removal of cured coating/adhesive

### HANDLING INFORMATION

1. Work Life, after thaw @ 25°C, 200 gm mass, hrs. > 8

Note: To thaw remove sealed container from freezer and allow to warm to room temperature. Leave cap on until ready to use. Do not place in oven or microwave to thaw - this will shorten work life. Typical time to thaw 8 oz bottle is approximately 30 minutes.

2. Once thawed, material is ready for use. For automated dispensing equipment pour amount needed into reservoir and purge with dry air, nitrogen, or argon. Unused material may be refrozen - however, purge with argon, nitrogen, or dry air prior to resealing and placement into freezer @ -40°C or below to minimize moisture contamination, premature polymerization, and degradation of the material's performance.

Note: User to determine if refrozen material is suitable for subsequent operation. Solvent evaporation may have occurred after first use; therefore, additional thinner may be required to achieve desired viscosity.

3. Work life adversely affected by heat and humidity as well as solvent evaporation.
4. Work life can be extended by additions of thinner and/or periodical replenishment of freshly mixed **UVIKOTE 7503LM-PMF**.
5. Bottles of **UVIKOTE 7503LM-PMF** are shipped in dry ice. Upon receipt transfer frozen containers to a storage freezer @ -40°C or below.
6. For thin, wet coatings ( $\leq 3$  mils), only minimal solvent evaporation dwell time (5-10 minutes) is usually required prior to UV exposure; whereas, thicker coatings may require a 15-30 minute dwell time to avoid a wrinkled surface or the presence of bubbles/erruptions after UV exposure. Customer to test for each application to determine if solvent dwell time is necessary and if so, for how long.

### CURE SCHEDULE

#### **U.V. Cure with Conveyor Equipment**

3-4 passes under 300 W/in Fusion UV, D-bulb lamp at rate of 2 feet per min. OR 2-3 passes under 300 W/in fusion UV, D-bulb @ rate of 1 foot per min. Bulb height above coating surface should be adjusted to expose the resin system to approximately  $\sim 17.5$  joules/cm<sup>2</sup> of radiation per pass at 1 foot/minute and  $\sim 12$  joules/cm<sup>2</sup> of radiation per pass at 2 feet/minute. The minimum total amount of joules that needs to be achieved to fully UV-cure this product is  $\geq 36$  joules.

#### **U.V. Cure with Spot Cure Equipment**

We recommend using an EFOS Novacure or equivalent equipment with similar power generating capabilities. This system is capable of generating the same amount of energy as in cure #1. In some applications, diffusers may be necessary to insure even energy distribution and complete cure. Customer should consult Aptek Laboratories and/or equipment supplier to optimize cure for individual applications.

#### **Postcure**

After curing as indicated in steps 1 or 2 above, the coating can be postcured as follows:

- a) 14 days at 25°C and 50% relative humidity  
OR
- b) 4 hours at 100°C, or 6 hours at 85°C, or 12 hours at 65°C

## Notes:

- 1) The above cure schedules are conservative and should be used as guidelines only. User should determine proper cure schedule based on application requirements and properties desired.
- 2) Cured material exposed to excess heat and long term aging may darken in color over time. Please note that this is a natural occurrence and no adverse effects to mechanical or electrical properties take place.

**TYPICAL PROPERTIES**  
(not for specification purposes)

<b><u>CHARACTERISTICS</u></b>	<b><u>7503LM-PMF</u></b>	<b><u>TEST METHOD</u></b>
Color	Slightly haze, yellow/amber	Visual
Specific gravity	0.89	ASTM D-1475
Viscosity @ 25°C,cps		ASTM D-1824
-Brookfield RVT, spindle #1, speed 100rpm	40	
-Brookfield LVT, spindle #60, speed 61rpm	14	
Flash point, °C	>100°C	TCC
Shelf life @-40°C, or below, months in factory sealed containers	6	
<b><u>CURED PHYSICAL PROPERTIES</u></b>	<b><u>7503LM-PMF</u></b>	<b><u>TEST METHOD</u></b>
Hardness, Durometer A	55A	ASTM D-2240
Glass transition temp., °C	-55	ASTM E831-86
Thermal coefficient of expansion, in/in/°C		
alpha 1	$82 \times 10^{-6}$	ASTM E831-86
alpha 2	$222 \times 10^{-6}$	
Outgassing @ $10^{-6}$ Torr		
TML, %	0.80	ASTM E-595
CVCM, %	0.02	ASTM E-595
Young's modulus, psi		
@55°C	450	
@25°C	700	
@-40°C	9500	
Evidence of haze	None	ASTM E-595
Fungus resistance	Non-nutrient	ASTM G-21
<b><u>CURED ELECTRICAL PROPERTIES</u></b>	<b><u>7503LM-PMF</u></b>	<b><u>TEST METHOD</u></b>
Volume resistivity, @25°C, ohm-cm*	$4.0 \times 10^{14}$	ASTM D-257
Dielectric constant, @1KHz, @25°C*	3.2	ASTM D-150
Dissipation factor @1KHz, @25°C*	0.03	ASTM D-150
Dielectric strength, 0.003" thick*		

film, volts/mil	>1500	ASTM D-149
Insulation resistance, ohms	$1.0 \times 10^{14}$	MIL-I-46058C

\* Tested on unsolvated castings @ 0.100" thickness

### **SAFETY AND FIRST AID**

**UVIKOTE 7503LM-PMF** is an unfilled organic polyol isocyanate/acrylate blend resin containing solvent and is thus considered a flammable liquid and should be treated with caution. Store @ -40°C or below and keep away from flame, sparks, or other sources of ignition. Use in well-ventilated area and avoid breathing vapors. In case of eye contact, flush with fresh clean water for at least 15 minutes; for skin contact, wash thoroughly with soap and water. If swallowed, drink at least one pint of water and call a physician. Refer to Material Safety Data Sheet for more details.

Current Revision: 04/24/2017 – dh

**APTEK**<sup>®</sup> is a registered trademark of Aptek Laboratories, Inc.

**UVIKOTE**<sup>™</sup> is a trademark of Aptek Laboratories, Inc

**UVISTAKE**<sup>™</sup> is a trademark of Aptek Laboratories, Inc.