



APTEK LABORATORIES, INC.

ISO 9001 / AS9100 Certified

28570 Livingston Avenue, Valencia, CA 91355-4171 • (661) 257-1677 FAX (661) 257-8939

TECHNICAL DATA & INFORMATION

UVIKOTE™ 7504LM-PMF

UV Curing, Low Modulus, Low Outgassing, Urethane Conformal Encapsulant/Coating

PRODUCT DESCRIPTION

UVIKOTE 7504LM-PMF is 100% solids, medium viscosity, one component, premixed frozen liquid, electrically insulating, transparent, urethane coating designed for the encapsulation and protection of electrical/electronic components mounted on printed circuit boards. This system provides an excellent combination of flexibility and low modulus for demanding applications where the management of thermomechanical stresses is required.

UVIKOTE 7504LM-PMF coating will become tack free when exposed to the proper UV light radiation. The coating will fully post cure in both the exposed and shaded areas in 14 days at 25°C and 50% relative humidity. As an alternative, the post cure for the coating in both exposed and shaded areas may be accelerated with low to moderate heat.

KEY FEATURES AND BENEFITS

- Qualified to Mil-I-46058C and IPC-CC-830B
- Multicure mechanism for complete cure in shaded areas underneath components
- Excellent flexibility and low modulus for reduced stress in the encapsulation of sensitive components (e.g. glass-bodied diodes)
- Meets NASA condensable volatile requirements for high vacuum environments
- Highly reversion resistant for good physical stability under high heat and humidity environments
- Low Tg (-65°C) for excellent low temperature cycling, storage and performance
- Excellent adhesion to plastic/metal components and substrates. Adheres well to itself for multicoat and repair applications
- Available in pre-mixed frozen syringes for convenient dispensing. Plungers available for hand operation or pneumatic-type syringes for automated dispensing.
- Ready-to-pour viscosity and long pot life for encapsulation, potting, and thick coating applications
- No TDI, no toxic solvents, no free acrylic acid for safety
- Complete companion UV product line available:
 - UVIKOTE 7503LM-PMF - low viscosity, sprayable version for circuit board coatings of ≤3 mils
 - UVISTAKE™7205LM-PMF - thixotropic, non-flow adhesive for wire tacking and component staking

- DISCLAIMER NOTICE -

All statements, technical data, and recommendations expressed herein are based on tests believed to be reliable and accurate. However, APTEK LABORATORIES, INC. gives no warranty, expressed or implied, regarding the accuracy of this information. It is intended that the buyer and user of these products shall determine the suitability of the information provided for his specific application, and is responsible for its selection.

APTEK LABORATORIES, INC. shall not be liable for any injury, loss or damage, direct or consequential, arising out of the use or misuse of these products, or of the information given in these data bulletins. Purchasers assume all risk and liability whatsoever in connection with the use of these products and this information.

- UVIKOTE T-100 Thinner - non-photosensitive, non-aromatic
- UVIKOTE S-100 Stripper - low viscosity removal of cured coating/adhesive for repair operations
- UVIKOTE S-200 Stripper - thixotropic version for localized removal of cured coating/adhesive

HANDLING INFORMATION

Work Life, after thaw @ 25°C, 10 gm mass, hrs. > 8

Note: - To thaw remove syringe from freezer and allow to warm to room temperature. Do not place in oven or microwave to thaw - this will shorten work life. Typical time to thaw 10cc syringe is approximately 15 minutes.

- Work life adversely affected by heat and humidity.
- Syringes of **UVIKOTE 7504LM-PMF** are shipped in dry ice. Upon receipt transfer frozen syringes to a storage freezer @ -40°C or below.

CURE SCHEDULE

U.V. Cure with Conveyor Equipment

3-4 passes under 300 W/in Fusion UV, D-bulb lamp at rate of 2 feet per min. OR 2-3 passes under 300 W/in fusion UV, D-bulb @ rate of 1 foot per min. Bulb height above coating surface should be adjusted to expose the resin system to approximately ~17.5 joules/cm² of radiation per pass at 1 foot/minute and ~12 joules/cm² of radiation per pass at 2 feet/minute. The minimum total amount of joules that needs to be achieved to fully UV-cure this product is ≥36 joules.

U.V. Cure with Spot Cure Equipment

We recommend using an EFOS Novacure or equivalent equipment with similar power generating capabilities. This system is capable of generating the same amount of energy as in cure #1. In some applications, diffusers may be necessary to insure even energy distribution and complete cure. Customer should consult Aptek Laboratories and/or equipment supplier to optimize cure for individual applications.

Postcure

After curing as indicated in steps 1 or 2 above, the coating can be postcured as follows:

- a) 14 days at 25°C and 50% relative humidity
OR
- b) 4 hours at 100°C, or 6 hours at 85°C, or 12 hours at 65°C

Note:

- 1) The above cure schedules are conservative and should be used as guidelines only. User should determine proper cure schedule based on application requirements and properties desired.
- 2) Cured material exposed to excess heat and long term aging may darken in color over time. Please note that this is a natural occurrence and no adverse effects to mechanical or electrical properties take place.

TYPICAL PROPERTIES

(not for specification purposes)

| <u>CHARACTERISTICS</u> | <u>7504LM-PMF</u> | <u>TEST METHOD</u> |
|-------------------------------|--------------------------|---------------------------|
| Color | Clear yellow/amber | Visual |
| Specific gravity | 0.94 | ASTM D-1475 |

| | | |
|---|----------------|-------------|
| Viscosity @ 25°C ± 3°C, cps | 5,000 – 25,000 | ASTM D-1824 |
| Flash point, °C | >100°C | TCC |
| Shelf life @ -40°C, or below, months factory sealed containers | 6 | |

| | | |
|---|--------------------------|---------------------------|
| <u>CURED PHYSICAL PROPERTIES</u> | <u>7504LM-PMF</u> | <u>TEST METHOD</u> |
|---|--------------------------|---------------------------|

| | | |
|--|------------------------|--------------|
| Hardness, Durometer A | 55A | ASTM D-2240 |
| Glass transition temp., °C | -55 | ASTM E831-86 |
| Thermal coefficient of expansion, in/in/°C | | |
| alpha 1 | 82 x 10 ⁻⁶ | ASTM E831-86 |
| alpha 2 | 222 x 10 ⁻⁶ | |
| Outgassing @ 10 ⁻⁶ Torr | | |
| TML, % | 0.80 | ASTM E-595 |
| CVCM, % | 0.02 | ASTM E-595 |
| Young's modulus, psi, | | |
| @55°C | 450 | |
| @25°C | 700 | |
| @-40°C | 9500 | |

| | | |
|-------------------|--------------|------------|
| Evidence of haze | None | ASTM E-595 |
| Fungus resistance | Non-nutrient | ASTM G-21 |

| | | |
|---|--------------------------|---------------------------|
| <u>CURED ELECTRICAL PROPERTIES</u> | <u>7504LM-PMF</u> | <u>TEST METHOD</u> |
|---|--------------------------|---------------------------|

| | | |
|--|------------------------|--------------|
| Volume resistivity, @25°C, ohm-cm | 4.0 x 10 ¹⁴ | ASTM D-257 |
| Dielectric constant, @1KH _z , @25°C | 3.2 | ASTM D-150 |
| Dissipation factor @1KH _z , @25°C | 0.03 | ASTM D-150 |
| Dielectric strength, 0.003" thick film, volts/mil | >1500 | ASTM D-149 |
| Insulation resistance, ohms | 1.0 x 10 ¹⁴ | MIL-I-46058C |

SAFETY AND FIRST AID

UVIKOTE 7504LM-PMF is an unfilled organic polyol isocyanate/acrylate resin blend and is considered safe to use when handled properly. Store at -40°C or below and keep away from flame, sparks, or other sources of ignition. Use in well-ventilated area and avoid breathing vapors. In case of eye contact, flush with fresh clean water for at least 15 minutes; for skin contact, wash thoroughly with soap and water. If swallowed, drink at least one pint of water and call a physician. Refer to Material Safety Data Sheet for more details.

Revised: 04/24/17 – dh

Issued: 3/6/01

APTEK® is a registered trademark of Aptek Laboratories, Inc.

UVIKOTE™ is a trademark of Aptek Laboratories, Inc

UVISTAKE™ is a trademark of Aptek Laboratories, Inc.