



APTEK LABORATORIES, INC.

ISO 9001 / AS9100 Certified

28570 Livingston Avenue, Valencia, CA 91355-4171 • (661) 257-1677 FAX (661) 257-8939

PRELIMINARY TECHNICAL DATA & INFORMATION

APTEK 95507

White, High Temperature Paint

PRODUCT DESCRIPTION

APTEK 95507 is a one component, white, semi-rigid, mineral-filled, silicone-based coating/paint designed for very high temperature space applications. A thin coating of **APTEK 95507** was developed to withstand long term exposures up to 500°C (932°F) without cracking or peeling with a good degree of adhesion and flexibility.

KEY FEATURES AND BENEFITS

- Supplied as a low viscosity sprayable paint for convenience.
- Passes NASA outgassing per ASTM-E 595

HANDLING INFORMATION

1. **APTEK 95507** is a one component, ready-to-spray system..
2. Filler will settle upon long term storage. Homogenize prior to use by vigorously shaking the sealed container or stirring by hand or mechanical means until uniform.
3. Once uniform, pour freshly agitated **APTEK 95507** into spray gun reservoir. For best results, keep mixture in spray reservoir stirred or shaken during spraying procedure.
4. SURFACE PREPARATION
 - a. Substrate surface to be sprayed should be clean and dry and free from mineral, petroleum oils/greases, etc.
 - b. It is recommended substrates be scrubbed with an abrasive cleaner, such as AJAX oxygen bleach and a red Scotchbrite® pad. An alternative cleaning process would be to abrade with 60-80 grit sand paper or to sandblast the surface with coarse grain to get a roughened surface for mechanical adhesion.
 - c. Then rinse with distilled water until a uniform 'sheet' of water film appears on surface. Rinse in clean, anhydrous IPA, and allow to air dry for 15 minutes. Then bake for 15 minutes @ 65°C in an air circulating oven.
5. PAINT APPLICATION: For optimum adhesion, flexibility, and high temperature performance, a cured film thickness of 0.0015" to 0.003" is recommended. Thicknesses above 0.0025" may result in loss of adhesion and/or flexibility.

- DISCLAIMER NOTICE -

All statements, technical data, and recommendations expressed herein are based on tests believed to be reliable and accurate. However, APTEK LABORATORIES, INC. gives no warranty, expressed or implied, regarding the accuracy of this information. It is intended that the buyer and user of these products shall determine the suitability of the information provided for his specific application, and is responsible for its selection.

APTEK LABORATORIES, INC. shall not be liable for any injury, loss or damage, direct or consequential, arising out of the use or misuse of these products, or of the information given in these data bulletins. Purchasers assume all risk and liability whatsoever in connection with the use of these products and this information.

CURE SCHEDULE

Solvent flash-off: 15 minutes @ RT (25°C) plus 30 mins @ 100°C,
 plus 1 hr @ 260°C,
 plus 1 hr @ 430°C,

plus allow to cool to RT gradually (DO NOT SHOCK COOL), preferably at a rate no faster than 1°C/minute until temperature drops below 100°C.

Cure schedule is a guideline. User to determine actual cure for application.

TYPICAL PROPERTIES

(Values not to be used for specification purposes.)

<u>CHARACTERISTICS</u>	<u>95507</u>	<u>TEST METHOD</u>
Color	White	Visual
Specific Gravity	1.25	ASTM D-1475
Viscosity @ 25°C, cps, Spindle 2, Speed 100 rpm	50	ASTM-D-1824
Flash point, °F	10	PMCC
Shelf life, months @ 5°C in factory sealed containers	6	
<u>CURED PHYSICAL PROPERTIES</u>	<u>2554</u>	<u>TEST METHOD</u>
Solar Absorptance, alpha	0.18 @ 0.0015" 0.14 @ 0.0030"	ASTM E-903
Total normal emittance	0.8	ASTM E-408
Outgassing @ 10 ⁻⁶ torr, TML, % CVCM, %	<1.0% <0.1%	ASTM E-595
Adhesion, with 3M 250 tape	Pass	ASTM D-3359

SAFETY AND FIRST AID

APTEK 95507 is a solvated, filled, silicone-based low viscosity coating which is safe to handle when used properly. Store the coating at 15-30°C in original factory sealed containers. In case of eye contact, flush with fresh clean water for at least 15 minutes; for skin contact wash thoroughly with soap and water. If swallowed, drink at least one pint of water and call a physician. Refer to MSDS for more details.

Issued: 6-28-23– mjb

APTEK® is a registered trademark of Aptek Laboratories, Inc.