



APTEK LABORATORIES, INC.

ISO 9001 / AS9100 Certified

28570 Livingston Avenue, Valencia, CA 91355-4171 • (661) 257-1677 FAX (661) 257-8939

TECHNICAL DATA & INFORMATION

APTEK® 2214-A/B

Space Grade, Low Modulus Urethane ESD Coating/Adhesive

PRODUCT DESCRIPTION

APTEK 2214-A/B is a carbon-filled, thixotropic, two component, electrically conductive, flexible urethane coating/adhesive designed to dissipate an electrostatic charge. This low-outgassing system provides a combination of high flexibility and good tensile strength/elongation characteristics.

KEY FEATURES AND BENEFITS

- Capable of full cure at RT for application where heat cure is not desired or possible
- Exceeds NASA outgassing requirements for space applications
- Non-TDI based for safety
- Excellent reversion resistance for good physical stability under high heat and humidity environments
- Tg BELOW -60°C for excellent low temperature cycling, storage and performance
- Excellent substrate adhesion; superior to silicones
- Available in pre-measured kits to minimize handling

HANDLING INFORMATION

Mix ratio, parts by weight: 100 (2214-A) / 14 (2214-B)

Work life, 50 gm mass, @ 25°C, 50% RH, mins: 30

Notes:

1. Material may be workable/spreadable past 30 minutes; however, the best ESD properties are achieved when used by 30 minutes of pot life.
2. Work life will be affected by temperature, humidity, and degree of solvent evaporation.

Handling Notes:

- Material is a smooth, thixotropic consistency. If it is desired to reduce the mixed viscosity, dilute A/B mixture with reagent grade toluene as needed.
- APTEK 2214-B should be stored in tightly closed, factory sealed containers at a temperature of 25-35°C. At this temperature the product will remain liquid. Crystallization, cloudiness, or formation of an insoluble white precipitate which is the solid dimer of the liquid Part B may occur upon prolonged storage at temperatures below 20°C. The precipitate is not harmful; however, do not shake the bottle. Place unopened Part B bottles into an air circulating oven at 45-60°C until clear amber liquid is evident (white precipitate layer may also be present). For 8 oz. containers or smaller the liquid should clear up in less than 2 hours. Carefully remove bottles from oven

- DISCLAIMER NOTICE -

All statements, technical data, and recommendations expressed herein are based on tests believed to be reliable and accurate. However, APTEK LABORATORIES, INC. gives no warranty, expressed or implied, regarding the accuracy of this information. It is intended that the buyer and user of these products shall determine the suitability of the information provided for his specific application, and is responsible for its selection.

APTEK LABORATORIES, INC. shall not be liable for any injury, loss or damage, direct or consequential, arising out of the use or misuse of these products, or of the information given in these data bulletins. Purchasers assume all risk and liability whatsoever in connection with the use of these products and this information.

without disturbing contents. Decant clear liquid out of bottle without disturbing the precipitate.

- Use entire bottle of Part B for each application if possible. Unused portion must be blanketed with dry nitrogen or argon and resealed to avoid moisture contamination.

MIXING

Weigh 100 parts of APTEK 2214 Part A into a clean dry glass, metal, or plastic container and then add 14 parts of APTEK 2214 Part B. Machine mix on slow speed or hand stir with glass or metal stirrer until complete and thorough blending is achieved (which should take ~ 1 minute for complete homogenization. Care should be taken to avoid any source of moisture contamination or air entrapment during mix.

Note:

For best results and a bubble-free coating, vacuum mixture at less than 10 mm Hg for no more than 10 seconds after "break" to avoid boiling the solvent from the mixture. Note: due to the thixotropy of the mixture, an obvious "break" may not be noticeable where the material rises and naturally falls in the vacuum chamber. Therefore, vacuuming for ~2-3 minutes may be sufficient for this material.

CURE SCHEDULE

7 days at 25°C*
or
4-16 hrs @ RT + 2 hrs @ 85°C

* NOTE: After 24 hours at 25°C, a 5 mil film is cured enough to handle without being tacky. The surface resistivity will be approximately 5×10^6 ohms per square. Allow the full 7 day cure to achieve ultimate physical properties and meet the NASA outgassing requirements.

TYPICAL PROPERTIES

(values not to be used for specification purposes)

<u>CHARACTERISTICS</u>	<u>2214-A</u>	<u>2214-B</u>	<u>TEST METHOD</u>
Color	Black	Pale yellow to amber	Visual
Clarity	Opaque	Clear to hazy	
Specific gravity	0.96	1.22	ASTM D-1475
Viscosity @ 20°C, cps	Thixotropic paste	55	ASTM D-1824
Flash point, °C	10	200	ASTM D-92
Shelf life @ 25°C, months factory sealed containers	6	6	

Notes: Shelf life may be reduced once containers are opened and material is exposed to air and moisture. To preserve maximum use life, blanket the contents of the containers with dry nitrogen or argon before resealing.

<u>CURED PHYSICAL PROPERTIES</u>	<u>2214-A/B</u>	<u>TEST METHOD</u>
Hardness, Durometer A	60	ASTM D-2240
Tensile strength, psi	450	ASTM D-412
Elongation, %	300	ASTM D-412

Glass transition temp., °C	<-60	Perkin Elmer TS-2
Outgassing @ 10 ⁻⁶ Torr		
TML, %	0.59	ASTM-E-595
CVCM, %	0.04	ASTM-E-595
Fungus resistance	non-nutrient	ASTM-G-21

CURED ELECTRICAL PROPERTIES**2214-A/B****TEST METHOD**

Surface resistivity @ 25°C, 3 mil thick film, ohms/square @ 100 V Bias	3.5 x 10 ⁶	QCP-016-0110
--	-----------------------	--------------

SAFETY AND FIRST AID

APTEK 2214-A is a carbon-filled polyol resin containing solvent and is thus considered a flammable liquid and should be treated with caution. Avoid storage temperatures above 35°C and keep away from flame, sparks, or other sources of ignition. Use in well-ventilated area and avoid breathing vapors. In case of eye contact, flush with fresh clean water for at least 15 minutes; for skin contact, wash thoroughly with soap and water. If swallowed, drink at least one pint of water and call a physician. Refer to Material Safety Data Sheet for more details.

APTEK 2214-B is an organic isocyanate which may cause severe eye and skin irritation with direct contact. Inhalation of vapors may result in breathlessness, severe coughing, chest discomfort, and irritation of mucous membranes. Avoid skin and eye contact and use in a well-ventilated, hooded area. In case of eye contact, flush profusely with fresh clean water and contact a physician. For skin contact, wash thoroughly with soap and water. If inhaled, move subject to fresh air and provide water to drink. If swallowed, dilute with at least one pint water and contact physician immediately. Refer to Material Safety Data Sheet for more details.

Revised: 9/3/26 – jmv

APTEK® is a registered trademark of Aptek Laboratories, Inc.